

UYGULAMALAR

Güç dağıtım hatları için çıplak havai iletken olarak kullanılır. Sağlamlık-ağırlık oranlamasındaki zayıflığı dolayısıyla AAC uzun salınım mesafesi gerektirdiği için iletim hatlarında ve kırsal kesim dağıtım hatlarında kullanımı azdır. AAC salınım mesafesinin genellikle kısa fakat yüksek iletkenliğin gerekli olduğu kent alanlarında yaygın olarak kullanılmaktadır. Alüminyumun yüksek korozyon direnci AAC' yi sahil kesimlerinde tercih edilir iletken yapmıştır.

KURULUM

AAC tesisatı havaya kurulabilir. Şahısların güvenliğinin ve ürünün işlevselliğinin tesisattaki aksaklıklardan etkilenmemesi için yerel elektrik kodları ya da benzerleri tarafından gösterilen tesisat talimatlarının takip edilmesi tavsiye edilmektedir

STANDARTLAR

Düşük Gerilim (LV) Dağıtım Hatlarında kullanılan AAC genellikle IEC 1089 a göre üretilmektedir. CSA C49, ASTM B231, DIN 48201, BS 215, SFS 2410 ve NF kullanılan diğer standartlar arasında yer almaktadır. Ayrıca müşteri talepleri doğrultusunda da üretim yapılabilmektedir.

YAPI

Bu çıplak, eş merkezli ve bükülü iletken yuvarlak elektrolitik derece alüminyum tellerden yapılmaktadır ve merkezindeki tam yuvarlak telin çevresinin bir veya birkaç helezonik tel tabakası ile sarılması ile oluşmaktadır. Bu iletkenler istendiği takdirde kompakt iletkenler olarak da üretilebilir. Bu iletkenler yatay tabakalar halinde örülü çeşitli sayıda alüminyum tellerden oluşmaktadır. Tüm teller aynı nominal çaptadır. En çok kullanılan yapılar 7, 19, 37, 61 ve 91 telli olanlardır.

ÖZELLİKLER VE AVANTAJLAR

Bu iletken aynı zamanda Alüminyum Örülü İletken olarak da bilinir. Bu iletken elektrolitik olarak rafine edilmiş (E.C. Grade) 99,7% saflıkta alüminyumdan üretilmiştir. Bu iletken temel olarak kent alanlarında, salınım mesafesini kısa ve desteklerin yakın olduğu alanlarda kullanılır. AAC nihai kullanıma bağlı olarak bir ya da daha fazla alüminyum tel bükümünden oluşmaktadır. Bu iletkenler ayrıca yoğun olarak sahil kısımlarında kullanılır çünkü çok yüksek korozyon direnci mevcuttur. AAC iletkenler genellikle birincil ve ikincil elektrik dağıtım hatlarında çıplak havai iletken olarak kullanılır. Genellikle 1350-H19 alüminyum filmaşin'den soğuk çekme yöntemi ile elde edilir. AAC ampacity (akım oranı) nın sürdürülmesi gereken ve hafif iletkenin tercih edildiği ve iletken sağlamlığının kritik bir faktör olmadığı yerlerde kullanılır.

APPLICATIONS:

Used as bare overhead conductor for power distribution lines. Due to its relatively poor strength to weight ratio, AAC has limited application in Transmission Lines and rural distribution because of the long spans utilized. AAC is also extensively used in urban areas where spans are usually short, but high conductivity is required. The excellent corrosion resistance of aluminum has made AAC a conductor of choice in coastal areas.

INSTALLATION

AAC cable can be installed in air. It is recommended that the installation instructions indicated by the Local Electric Code, or any equivalent, be followed, so that the safeguarding of persons and the integrity of the product will not be affected by deficiencies in the installation.

SPECIFICATIONS:

AAC for Low Voltage (LV) Distribution Lines are usually manufactured according to IEC 1089. Sizes and stranding in accordance with other specification as CSA C49, ASTM B231, DIN 48201, BS 215, SFS 2410, NF or customer's specification can be manufactured by request.

CONSTRUCTION:

This bare concentric-lay stranded conductor, made from round electrolytic grade aluminum wires, is constructed with a straight round central wire surrounded with one or more layers of helically layed wires. These conductors are also manufactured as compact conductors if required. These conductors are formed by several wires of aluminium, stranded in concentric layers. All the wires have the same nominal diameter. Most common constructions consist of 7, 19, 37, 61 and 91 wires.

FEATURES AND BENEFITS:

This conductor is also known as aluminium stranded conductor. This conductor is manufactured from electrolytically refined (E.C.GRADE) aluminium, having purity of minimum 99.7% of aluminium. This conductor is used mainly in urban areas and the spacing is short and the supports are close. All aluminium conductors are made up of one or more strands of aluminium wire depending on the end usage. These conductors are also used extensively in costal because it has a very high degree of corrosion resistance. AAC All Aluminum Conductors are used as bare overhead conductor for primary and secondary power distribution lines are usually manufactured cold-drawing (hard or annealed) method from 1350-H19 aluminium rods. AAC is used where ampacity(Current Ratio) must be maintained and a lighter conductor (compared to ACSR) is desired, when conductor strength is not a critical factor.

TAM ALÜMİNYUM İLETKENLER
ALL ALUMINIUM CONDUCTORS (A.A.C.)

STANDARD TS IEC 1089

Kanada Standartındaki Adı Canada Standart Type	Kesit Cross Section			Tel Sayısı ve Çapları Number and Diameter of Wires No x Ømm	Komple İletken Çapı Diameter of Conductor mm	Kopma Mukavemeti Rated Strength kN	20°C'deki Direnci Electrical Resistance at 20°C Ohm/km	Birim Ağırlığı Unit Weight kg/km
		Komple iletken Overall Diameter mm ²	Bakır Eşdeğeri Copper Equivalent mm ²					
	AWG							
ROSE	4	21.14	13.30	7x1.96	5.88	416	1.3558	57.8
LILY	3	26.60	16.73	7x2.2	6.60	514	1.0776	72.8
IRIS	2	33.53	21.09	7x2.47	7.41	637	0.8537	91.8
PANSY	1	42.50	26.72	7x2.78	8.34	777	0.6743	116.8
POPPY	1/0	53.50	33.63	7x3.12	9.36	941	0.5354	146.4
ASTER	2/0	67.34	42.22	7x3.50	10.50	1185	0.4254	184.4
PHLOX	3/0	84.91	53.40	7x3.93	11.79	1435	0.3372	232.5
OXLIP	4/0	107.38	67.53	7x4.42	13.26	1814	0.2662	294.0
VALERIAN	250000	126.38	79.46	19x2.91	14.55	2261	0.2277	347.5
DAISY	266800	135.28	85.07	19x3.01	14.88	2421	0.2127	372.1
PEONY	300000	151.9	95.47	19x3.19	15.95	2671	0.1896	417.7

Merkez : Emekyemez Mah. Mürdüm Sk. No. 1 34420 Karaköy / İSTANBUL Tel. : (0212) 235 26 72 - 235 21 85 Fax : (0212) 237 63 23
Fabrika : İnkılap Mah. Dr. Fazıl Küçük Cd. No. 16 Ümraniye / İSTANBUL Tel. : (0216) 634 10 23 (7 Hat) Fax : (0216) 634 10 30
www.sahrakablo.com e-mail:sahra@sahrakablo.com